

Product description

Enkamat 7010 is a flexible three-dimensional matting, produced from polyamide 6 monofilaments welded together where they cross to form a tough, open structured matting with more than 95% free space. Mattings wider than 1 m are produced by thermally joining 1 m wide lanes.

Application

Enkamat 7010 is a proven, lightweight, flexible permanent erosion prevention mat. The three-dimensional structure of Enkamat 7010 provides an artificial root system for permanent reinforcement and helps nature to develop strong vegetation for permanent erosion protection of slopes, banks, landfills and other vulnerable erosion-prone areas.

Performances

Descriptive features

		Mean value	
Polymer		PA6	
Polymer density	kg/m ³	1140	
Colour		black	
Mass per unit area	g/m ²	260	EN 965
Nominal thickness	mm	10	
Soil retention factor	m/m ²	1810	Total length of filament per unit area

Mechanical properties

		Mean value	
Tensile strength MD	kN/m	1.5	EN 10319
Tensile strength CMD	kN/m	1.1	EN 10319
Tensile strength of the joints	kN/m	0.7	EN 10319

Thermal properties

		Classification	
Temperature resistance	°C	-30 to +80	no reduction in flexibility or strength

Dimensions and weights

Enkamat Standard	Mattings					Rolls		
	Thickness	Weight	Width	Length	Area	Ø	Length	Gross-weight
	mm	g/m ²	m	m	m ²	m	m	kg
7010/1	10	260	1.00	150	150	1.20	1.03	40

Individual values may vary from above mentioned data.

Enkamat 7010 can also be supplied 1.95 m and 3.85 m wide.

Quality Assurance



The Quality Management System of Colbond bv, at Arnhem (development and sales) and Obernburg (production), has been approved by Lloyd's Register Quality Assurance Limited for the ISO 9001:2000 quality management system standard (Certificate No. 935136).

Colbond bv, P.O. Box 9600, 6800 TC Arnhem, the Netherlands
Phone: +31 26 366 4600 • Fax: +31 26 366 5812
geosynthetics@colbond.com • www.colbond.com

The information set forth in this brochure reflects our best knowledge at the time of issue. The brochure is subject to change pursuant to new developments and findings, and a similar reservation applies to the properties of the products described. We undertake no liability for results obtained by usage of our products and information.